



## AMBANI ORGANICS PVT. LTD.

801, "351 – ICON", Andheri (E), Mumbai – 400069 ,India

Tele – 022 26833778 [www.ambaniorganics.com](http://www.ambaniorganics.com)

### AOPL 2259 STYRENE ACRYLIC 50%

<b>Chemical type</b>	: Styrene Acrylic
<b>Visula Appearance</b>	: Milky white
<b>Solid content</b>	: 48 +/- 2%
<b>Viscosity @ 30 C</b>	: 1000 - 2000 cps
<b>pH</b>	: 8 ~ 10
<b>Free monomer content</b>	: < 0.3%
<b>Tg.</b>	: 9 °C
<b>Properties</b>	<p>It has good wet and dry pick resistance, better heat and mechanical stability.</p> <p>: Very good sheets gloss, smoother surface, improved opacity and brightness, improved print gloss.</p>
<b>Recommended Applications</b>	<p>AOPL 2259 can be used as such or along with oxidized starch or casein as natural binders in coating formulations. It is compatible with china clay, calcium carbonate, whiting, titanium dioxide and most other standard pigments.</p> <p>: IT IS MAINLY USED FOR DUPLEX PAPER BOARD</p>

#### ISO: 9001 : 2008 Certified

The above information is to the best of our knowledge true and accurate. Since the conditions that the products are used in cannot be handled or controlled by us we cannot guarantee the results and assume liability to damages incurred by using this product  
Refer to M.S.D.S. for handling procedures.