

THE PIONEERS IN CNSL TECHNOLOGY

PPA - 7114

PHENALKAMIDE (PHENALKAMINE MODIFIED WITH POLYAMIDE) EPOXY HARDENER

Phenalkamide **PPA -7114** is a Mannich base reaction product. It shows rapid cure with workable pot life, superior corrosion resistant properties & adhesion to damp surfaces. It has longer pot life to card phenol based Phenalkamines. It offers superior resistance to humidity, acids, alkali, water, solvents & various chemicals.

Chemical Structure

OH
$$CH2 - NH = (CH_2)_2 - NH = CH_2 - NH = (CH_2)_2 - NH = CH_2 - NH = (CH_2)_2 - NH = CH_2 - NH = CH$$

R = H, ALKYL, ARYL

R' = MONOMERIC, DIMERIC OR POLYMER OF FATTY ACID

Features

- · Excellent rapid cure even at low temperatures
- Good chemical solvent & water resistance
- · Very good compatibility with
 - i) Epoxy resin based on bis- phenol A
 - ii) Epoxy resin based on bis- phenol F
 - iii) Epoxy resin based on novolacs
 - iv) Most of the organic solvents & their combinations
- Non-critical mixing ratios
- Excellent curing under humid & damp conditions
- · Good adhesion to mechanically cleaned surfaces
- Superior corrosion resistance
- Very good flexibility
- · Workable pot life

Applications

- · Solvent free, high solid coatings
- Pipeline & tank coatings
- Adhesives
- · Surface tolerant primers for metallic substrate
- Marine & industrial coatings

Revision No.: 4 Issue: Oct 2012 Page 1 / 3



THE PIONEERS IN CNSL TECHNOLOGY

Typical Properties

Sr. No.	Property	Unit	Typical Properties
i)	Appearance	Visual	Light Brown Viscous Liquid
ii)	Colour	Gardner	17 Max
iii)	N.V.M.	%	Min. 97
iv)	Amine Value	mg KOH/g	200 - 250
v)	Viscosity @ 25° C	cPs	100000 - 300000
vi)	Density @ 25° C	g / cm³	0.98 - 1.01
vii)	Flash Point (Closed Cup)	°C/°F	205 / 401
viii)	AHEW	g / eq.	220
ix)	Recommended PHR (EEW -190)		115

Formulation

Liquid Epoxy Resin (EEW - 190)	100
Paladin PPA - 7124	115

Optimum Curing Schedule 7 days at 25° C

Gel Time (100g @ 25° C) Mixing	45 - 55 min
----------------------------------	-------------

B.K Drying Recorder, set time, (200 microns) 8 mil (Liquid Epoxy Resin EEW - 190)

@ 25° C	2 - 4 hrs
@ 5° C	15 - 20 hrs
@ 0° C	-

Storage & Stability

Hardener **PPA** – **7114** should be stored in a cool dry place at 18 - 25° C in the sealed containers to achieve shelf life of minimum one year. Product can react with moisture & carbon dioxide in the air. This may result in increased viscosity & reduced activity.

Handling Precautions

May be harmful if ingested or absorbed through the skin & can cause sensitization. Will cause severe inflammation in contact with eye & skin. Wash thoroughly after handling. Adequate ventilation is essential during application. Containers should be tightly closed when not in use or during transportation. Do not inhale mist or vapours. It is recommended to use gloves, safety glasses & protective clothing for safe handling.

Revision No.: 4 Issue: Oct 2012 Page 2 / 3



THE PIONEERS IN CNSL TECHNOLOGY

First AID

In case of

Inhalation : Remove to fresh air & give oxygen if breathing is difficult.
 Ingestion : Give plenty of water. Do not induce vomiting. Contact a physician.
 Contact with eyes : Flush eyes with plenty of clean water for at least 15 minutes.

Contact with eyes: Flush eyes with plenty of clean water for at least 15 minutes. **Contact with skin**: Immediately wash with mild soap & water.

Declaimer

All information contained is based on practical experience. Our technical advice — whether verbal, written by way of trials are given in good faith. Neither warranty nor guarantee is offered or implied & accepted at the seller's risk, since the actual conditions prevailing at the time of using this product are outside the control of the company. Hence it is entirely buyer's & user's responsibility. While the information contained here in is believed to be reliable. **Paladin Paints & Chemicals Pvt. Ltd.** makes no representations as to the results the user or buyer will attain. Product performance & full scale testing are the responsibilities of the buyer & user.

Unit No-204, Monarch Chambers, Marol Maroshi Road, Marol Naka, Andheri (E), Mumbai 400 059, Maharashtra, India. **Phone**: (022) 29202587 / 29206258 . **Fax**: (022) 29254386 . **Email**: vanaprabha@vsnl.com

Revision No.: 4 Issue: Oct 2012 Page 3 / 3