


## THE PIONEERS IN CNSL TECHNOLOGY

# PPA - 7114 X 70

#### PHENALKAMIDE (PHENALKAMINE MODIFIED WITH POLYAMIDE) EPOXY HARDENER

Phenalkamide **PPA -7114 X 70** is a Mannich base reaction product supplied in xylene solution. It shows rapid cure with workable pot life, superior corrosion resistant properties & adhesion to damp surfaces. It has longer pot life to card phenol based Phenalkamines. It offers superior resistance to humidity, acids, alkali, water, solvents & various chemicals.

### **Chemical Structure**



R = H, ALKYL, ARYL

R' = MONOMERIC, DIMERIC OR POLYMER OF FATTY ACID

#### Features

- Excellent rapid cure even at low temperatures
- Good chemical solvent & water resistance
- Very good compatibility with
  - i) Epoxy resin based on bis- phenol A
  - ii) Epoxy resin based on bis- phenol F
  - iii) Epoxy resin based on novolacs
  - iv) Most of the organic solvents & their combinations
- Non-critical mixing ratios
- Excellent curing under humid & damp conditions
- · Good adhesion to mechanically cleaned surfaces
- Superior corrosion resistance
- Very good flexibility
- Workable pot life

## **Applications**

- Solvent free, high solid coatings
- Pipeline & tank coatings
- Adhesives
- Surface tolerant primers for metallic substrate
- Marine & industrial coatings



Paladin Paints & Chemicals Pvt. Ltd.

# THE PIONEERS IN CNSL TECHNOLOGY

## **Typical Properties**

| Sr. No. | Property                   | Unit                | Typical Properties<br>Light Brown Viscous Liquid |  |
|---------|----------------------------|---------------------|--|--|
| i)      | Appearance                 | Visual              |  |  |
| ii)     | Colour                     | Gardner 17 Max      |  |  |
| iii)    | N.V.M.                     | %                   | 70 <u>+</u> 2                                    |  |
| iv)     | Amine Value                | mg KOH/g            | 145 - 185  |  |
| V)      | Viscosity @ 25° C          | cPs                 | 500 - 1500                                       |  |
| vi)     | Density @ 25° C            | g / cm <sup>3</sup> | 0.98 <u>+</u> 0.01                               |  |
| vii)    | Flash Point (Closed Cup )  | °C / °F             | 28 / 82.4  |  |
| viii)   | AHEW                       | g / eq.             | 300  |  |
| ix)     | Recommended PHR (EEW -190) |                     | 158  |  |

#### Formulation

| Liquid Epoxy Resin ( EEW - 190 ) | 100 |
|----------------------------------|-----|
| Paladin PPA – 7114 X 70          | 158 |

Optimum Curing Schedule 7 days at 25° C

| Gel Time ( 100g @ 25° C ) Mixing | 155 min. |
|----------------------------------|----------|
|                                  |          |

## B.K Drying Recorder, set time, (200 microns) 8 mil

(Liquid Epoxy Resin EEW - 190)

| @ 25° C | 3 - 5 hrs   |
|---------|-------------|
| @ 5° C  | 16 - 18 hrs |
| @ 0° C  | -           |

### Storage & Stability

Hardener **PPA** – **7114 X 70** should be stored in a cool dry place at 18 - 25° C in the sealed containers to achieve shelf life of minimum one year. Product can react with moisture & carbon dioxide in the air. This may result in increased viscosity & reduced activity.

#### **Handling Precautions**

May be harmful if ingested or absorbed through the skin & can cause sensitization. Will cause severe inflammation in contact with eye & skin. Wash thoroughly after handling. Adequate ventilation is essential during application. Containers should be tightly closed when not in use or during transportation. Do not inhale mist or vapours. It is recommended to use gloves, safety glasses & protective clothing for safe handling.



## THE PIONEERS IN CNSL TECHNOLOGY

## **First AID**

Paladin

Paints & Chemicals Pvt. Ltd.

| In case of<br>Inhalation<br>Ingestion<br>Contact with eyes<br>Contact with skin |  | Remove to fresh air & give oxygen if breathing is difficult.<br>Give plenty of water. Do not induce vomiting. Contact a physician.<br>Flush eyes with plenty of clean water for at least 15 minutes.<br>Immediately wash with mild soap & water. |
|---|--|--|
|---|--|--|

### Declaimer

All information contained is based on practical experience. Our technical advice – whether verbal, written by way of trials are given in good faith. Neither warranty nor guarantee is offered or implied & accepted at the seller's risk, since the actual conditions prevailing at the time of using this product are outside the control of the company. Hence it is entirely buyer's & user's responsibility. While the information contained here in is believed to be reliable. **Paladin Paints & Chemicals Pvt. Ltd.** makes no representations as to the results the user or buyer will attain. Product performance & full scale testing are the responsibilities of the buyer & user.

Paladin Paints & Chemicals Pvt. Ltd. Unit No-204, Monarch Chambers, Marol Maroshi Road, Marol Naka, Andheri (E), Mumbai 400 059, Maharashtra, India. Phone : (022) 29202587 / 29206258 . Fax : (022) 29254386 . Email : vanaprabha@vsnl.com