



## Technical Data Sheet

### STRUCK - N (CPVL)

**Composition** : Celluloid Preparation with aqueous potassium soap.

**Specification** : Appearance : Pale Yellow gel.  
pH : 10-11  
Soild Content : 30 ± 2%

**Dosage** :

- For soft compounds like sponge compound sheets concentration of 1 part by weight Struck - N (CPVL) in 8 parts by weight of water can be used.
- Extruded hoses can be dipped in an aqueous solution of 1 part by weight of Struck N in 4 to 9 part by weight of water.

**Uses and Benefits** :

- Used as an anti-tack agent for uncured rubber sheets of mixed compounds.
- It prevents sticking of compounded sheets, semi-finished goods and extruded articles to each other.
- Struck - N (CPVL) is to be used in diluted form.
- It is to be diluted with water to get desired concentration.
- This Aqueous solution can be used by spraying, Brushing, Dipping.

**Packing** : 50 kg / 200 kg MS drum.

**Storage stability** : Up to 1 years In normal storage conditions

**Handling** : Consult material safety data sheet (MSDS) for additional handling information for Struck – N (CPVL).

#### PUKHRAJ ADDITIVES LLP

*An ISO 9001:2008 Certified Company*

5B, 5<sup>th</sup> Floor, Diamond House, Plot No. 515, Behind National College,  
TPS III, 35<sup>th</sup> Road, Bandra (W), Mumbai, Maharashtra - 400 050 (INDIA).

Tel: +91-9833538089/+91-22-26494911/26494912/26494913

Email: [info@pukhrajzinculet.com](mailto:info@pukhrajzinculet.com) Visit us at: [www.pukhrajzinculet.com](http://www.pukhrajzinculet.com)