



STRUCK - N

Composition : Celluloid Preparation of Salt of Oleic Acids and Amides. Does not contain any petroleum/Bituminous Oil.

Specification	:		25 %	30 %
-	Appearance	:	Pale White free	Pale White free
			flowing liquid.	flowing liquid.
	pН	:	9 -10	9-10
	Soild Content	:	$25 \pm 2\%$	30 ± 2%

Dosages

- For soft compounds like sponge compound sheets concentration of 1 part by weight Struck N in 5 parts by weight of water can be used.
- Extruded hoses can be dipped in an aqueous solution of 1 part by weight of Struck N in 3 to 6 part by weight of water.

Uses and Benefits

:

- Used as an anti-tack agent for uncured rubber sheets of mixed compounds.
- It prevents sticking of compounded sheets, semi-finished goods and extruded articles to each other.

Application

:

- Struck N is to be used in diluted form.
- It is to be diluted with water to get desired concentration.
- This Aqueous solution can be used by spraying, Brushing, Dipping.
- Packing : 50kg or 200kg MS drum.

Storage stability	:	Up to 1 years in normal storage conditions.
-------------------	---	---

- Approvals : SVHC
- **Handling** : Consult material safety data sheet (MSDS) for additional handling information for Struck N.

PUKHRAJ ADDITIVES LLP

<u>An ISO 9001:2008 Certified Company</u> 5B, 5th Floor, Diamond House, Plot No. 515, Behind National College, TPS III, 35th Road, Bandra (W), Mumbai, Maharashtra - 400 050 (INDIA). Tel: +91-9833538089/+91-22-26494911/26494912/26494913

Email: info@pukhrajzincolet.com Visit us at: www.pukhrajzincolet.com

Information provided herein is based upon tests believed to be reliable. We have no control over the manner in which others may use this information, it does not guarantee the results to be obtained. The company assumes no obligation or liability for the information in this document. No warranties are given, all implied warranties of merchantability or fitness for a particular purpose are expressly excluded.

March 2016