



Technical Data Sheet

Pentoflex – SP (P)

Antioxidant

Composition : Styrenated Phenol blended with inorganic filler

Specification :

Color	: Light Creamish to White
Appearance	: Powder
Ash Content	: 50 % Min
Heat Loss	: 2 % Max

Dosage :

- 1.5 – 3.5 phr

Uses and Benefits :

- Pentoflex – SP (P) is a very widely used and inexpensive non-staining, non discoloring antioxidant for white / colored or transparent rubber products based on NR, IR, SBR, BR, NBR, CR, etc.
- Pentoflex – SP (P) also finds applications as a stabilizer for synthetic rubbers and plastics such as Polypropylene, Polyethylene, high impact polystyrene.
- Pentoflex – SP (P) disperses very easily in dry rubber compounds and does not bloom or affect the color, odor and transparency of the rubber product.
- Pentoflex – SP (P) does not influence the viscosity, scorch and cure characteristics of rubber compounds nor does it have any influence on unaged mechanical properties of rubber vulcanizates.
- Pentoflex – SP (P) offers good oxidation, heat and ozone resistance as well as flex fatigue resistance to transparent / white / colored rubber vulcanizates and exhibits good 'Color fastness' characteristics.
- The combination of Pentoflex – SP (P) and antioxidant Pentoflex – TDQ offer synergistic effect to improve the heat ageing resistance of rubber vulcanizates at lower cost but with only slight discoloration.
- Pentoflex – SP (P) is a suitable antioxidant for normal as well as heat sensitized NR latex based compounds and its performance in NR latex based vulcanizates is similar to that of NR dry rubber based vulcanizates.

Packing : 25kg Polylinedpolywoven bag / Polylined paper bag.

Storage stability : Up to 1 year in normal storage conditions.

Handling : Consult material safety data sheet (MSDS) for additional handling information for Pentoflex – SP (P).

PUKHRAJ ADDITIVES LLP

An ISO 9001:2008 Certified Company

5B, 5th Floor, Diamond House, Plot No. 515, Behind National College,
TPS III, 35th Road, Bandra (W), Mumbai, Maharashtra - 400 050 (INDIA).

Tel: +91-9833538089/+91-22-26494911/26494912/26494913

Email: info@pukhrajzinculet.com Visit us at: www.pukhrajzinculet.com